



CHEMICAL & STAIN RESISTANCE DATA REPORT

HERO LVT 2.5MM & HERO LVT 5MM

Staining Agent	5 Minute Ratings			24 Hour Ratings		
	Surface Dulling	Surface Attack	Color Change	Surface Dulling	Surface Attack	Color Change
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	1	0	0	1	0	0
Gasoline	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

Rating Key

- 0 - No Change
- 1 - Slight Change
- 2 - Moderate Change
- 3- Severe Change