

## FEATURES

RECYCLED RUBBER FROM ATHLETIC SHOES

ZERO TIRES, ZERO TIRE ODOR

APPROVED FOR AREAS WITH FREE WEIGHTS WHEN USING 8MM THICKNESS OR GREATER

65% NIKE GRIND

## COLORS



**HERO**  
RUBBER

MADE WITH



NIKE GRIND

## TECHNICAL INFORMATION

| SPECS                                        | TEST       | HERO VALUES                                                                                         |
|----------------------------------------------|------------|-----------------------------------------------------------------------------------------------------|
| SOUND ABSORPTION/NOISE REDUCTION COEFFICIENT | ASTM C423  | SAA - 0.04<br>NRC - 0.05                                                                            |
| TABER ABRASION                               | ASTM C501  | Weight Loss 0.92 grams (1.39%)                                                                      |
| COMPRESSION SET UNDER FORCE                  | ASTM D395B | 82.2% Recovered; 17.8% Unrecovered                                                                  |
| BREAKING LOAD AND ELONGATION                 | ASTM D412  | Elongation - 48.71%<br>Tensile - 204.4 lbs/sq. in.                                                  |
| STATIC COEFFICIENT OF FRICTION               | ASTM D2047 | Dry 0.78                                                                                            |
| HARDNESS SHORE A DUROMETER                   | ASTM D2240 | 65                                                                                                  |
| IMPACT SOUND TRANSMISSION                    | ASTM E492  | IIC 58                                                                                              |
| FLEXIBILITY                                  | ASTM F137  | 6mm Mandrel PASS                                                                                    |
| ELECTRICAL RESISTANCE - SURFACE TO GROUND    | ASTM F150  | 4.0 x 10 <sup>10</sup> ohms (average)                                                               |
| ELECTRICAL RESISTANCE - SURFACE TO SURFACE   | ASTM F150  | 2.8 x 10 <sup>11</sup> ohms (average)                                                               |
| RESISTANCE TO CHEMICALS (5 MIN & 24 HR)      | ASTM F925  | Slight to Moderate Color Change from 5% Acetic Acid, Mineral Oil, 5% Phenol, Kerosene and Olive Oil |
| STATIC LOAD (250 LBS)                        | ASTM F970  | 0.009 inch residual compression                                                                     |
| SHORT TERM INDENTATION (140 LBS)             | ASTM F1914 | -0.064 inch residual indentation                                                                    |

## SIZES

24"x24" Square/Interlocking  
24"x36" Square  
24"x72" Square  
38"x38" Square/Interlocking  
48"x72" Square/Interlocking

24"x24"

24"x36"

24"x72"

38"x38"

48"x72"

## THICKNESS

4-19mm Square, 6-19mm Interlocking

## CERTIFICATION

Declare.

